

# KRYLON® INDUSTRIAL PAINT APPLICATION CHART

KRYLON PRODUCT	FORMULA	VOC/MIR COMPLIANT	HIDING	DURABILITY	DRY TIME TO TOUCH	RECOAT WINDOW	CLEAN-UP	CORROSION RESISTANCE	GLOSS	GASOLINE & OIL RESISTANCE
<b>Rust Tough®</b>	Modified Acrylic Enamel	Yes	Best	Best	25 minutes	Before 2 hours or after 2 days	Mineral spirits, turpentine (wet). When dry, lacquer thinner, stripper.	Very good by itself. Excellent with primer	High	Film does not soften
<b>Rust Tough® Utili-Coat™</b>	Modified Acrylic Enamel	Yes	Best	Best	25 minutes	Before 2 hours or after 2 days	Mineral spirits, turpentine (wet). When dry, lacquer thinner, stripper.	Very good by itself. Excellent with primer	High	Film does not soften
<b>Eco-Guard®</b>	Acrylic Latex Enamel	Yes	Very Good	Very Good	20 minutes	Anytime	Soap & water (wet), Lacquer thinner, stripper when dry.	Good by itself. Excellent with primer	High	Film softens after 15 minutes
<b>Interior/Exterior (5-Ball)</b>	Acrylic Lacquerized Enamel	Yes	Good	Good	12 minutes	Anytime (not for use over acrylics)	Lacquer thinner	Excellent with primer.	Medium	Film softens after 15 minutes
<b>Fusion For Plastic®</b>	Modified Acrylic Alkyd	Yes	Very Good	Very Good	15 minutes	Before 24 hours or after 7 days	Lacquer or paint thinner	Very good by itself	High	Film softens after 15 minutes
<b>Tough Coat®</b>	Acrylic Enamel	Yes	Very Good	Very Good	15 minutes	Up to 4 hours or after 5 days	Mineral spirits, turpentine (wet). When dry, lacquer thinner, stripper.	Good by itself. Excellent with primer	High	Film softens after 15 minutes
<b>ColorWorks® Maintenance Choice™</b>	Acrylic Enamel	Yes	Good	Good	15 minutes	Before 4 hours or after 5 days	Mineral spirits, turpentine (wet). When dry, lacquer thinner, stripper.	Good by itself. Excellent with primer	High	Film softens after 15 minutes
<b>SparVar®</b>	Lacquerized Enamel	Yes	Good	Good	15 minutes	Anytime (not for use over acrylics)	Lacquer thinner	Excellent with primer.	Medium	Film softens after 15 minutes
<b>Paint-All®</b>	Acrylic Enamel	Yes	Good	Good	18 minutes	Up to 4 hours or after 5 days	Mineral spirits, turpentine (wet). When dry, lacquer thinner, stripper.	Good by itself. Excellent with primer	High	Film softens after 15 minutes
<b>Weekend®</b>	Acrylic Enamel	Yes	Good	Good	20 minutes	Up to 4 hours or after 5 days	Mineral spirits, turpentine (wet). When dry, lacquer thinner, stripper.	Good by itself. Excellent with primer	High	Film softens after 15 minutes
<b>Work Day™</b>	VT Alkyd	Yes	Good	Fair	15 minutes	Before 2 hours or after 3 days	Mineral spirits, turpentine (wet). When dry, lacquer thinner, stripper.	Fair by itself. Very good with anti-rust primer	High	Film softens after 15 minutes

