

Insulating Varnish Selection Guide

Product Characteristics						
Product #	Sprayon Product	Dielectric Strength	Class F	Dry Time	Color	Chemical Resistance
S00601	Red Insulating Varnish	2,100	Y	20 minutes	Red	Excellent
S00609	Green Epoxy Insulating Varnish	1,900	Y	1 hour	Green	Excellent
S00600	Clear Insulating Varnish	2,200	Y	10-15 minutes	Clear	Very Good
SB-6-665	Red Epoxy Insulating Enamel	1,100	Y	15 minutes	Red	Excellent
S07004	Schenectady Red Insulating Enamel	2,100	Y	20 minutes	Red	Excellent

Class F insulators will withstand temperatures up to 155°C. (310°F.)